

## **IN THE CLAIMS:**

The following is a complete listing of the claims and replaces all prior versions and listings of claims in the subject application. Please amend the claims as follows:

1.     **(Currently Amended)** A film comprising:  
a dimensionally stable, thin plastic film having a smooth surface finish; and  
a thin layer of non-molded silicone elastomer having a durometer of less than 30 on the Shore A scale disposed on a first surface of the plastic film, the silicone elastomer having a bubble pattern texture, each bubble of the bubble pattern texture having a height-to-diameter aspect ratio of less than 1.0.
2.     **(Original)** The film according to claim 1, wherein the plastic film is co-extruded, having a surface energy of less than about 40 Dynes/cm.
3.     **(Cancelled).**
4.     **(Original)** The film according to claim 1, further comprising:  
an adhesive disposed on a second surface of the plastic film.
5.     **(Original)** The film according to claim 4, further comprising:  
a releasable liner for covering the adhesive prior to use.
6.     **(Original)** The film according to claim 1, wherein the silicone elastomer has a polished surface finish.
7.     **(Original)** The film according to claim 6, wherein the polished surface finish is smooth.

8. **(Previously Presented)** The film according to claim 6, wherein the polished surface finish is textured.
9. **(Original)** The film according to claim 6, wherein the polished surface finish is formed by a casting means having a polished surface finish.
10. **(Original)** The film according to claim 1, wherein the silicone elastomer has a textured and polished surface finish.
11. **(Original)** The film according to claim 10, wherein the texture is an array of upraised dimples.
12. **(Previously Presented)** The film according to claim 1, wherein the silicone elastomer has a matte surface finish.
13. **(Previously Presented)** The film according to claim 1, wherein the plastic film is a heat stabilized plastic film.
14. **(Original)** The film according to claim 1, wherein the plastic film has a thickness of about 0.002 inches or less.
15. **(Original)** The film according to claim 1, wherein the plastic film is tinted.
16. **(Original)** The film according to claim 1, further comprising:  
graphical indicia associated with the plastic film.
17. **(Original)** The film according to claim 1, wherein the silicone elastomer is tinted.
18. **(Original)** The film according to claim 1, further comprising:  
graphical indicia associated with the silicone elastomer.

19. **(Original)** The film according to claim 1, wherein the film is configured for application on the fingertips of users.

20. **(Original)** The film according to claim 1, wherein the film is configured for application on handheld devices.

21. **(Original)** The film according to claim 1, wherein the film is configured for placement onto a material handling device.

22. **(Previously Presented)** The film according to claim 21, wherein the material handling device is a roller in a printer.

23. **(Original)** The film according to claim 1, wherein the film is configured for use on equipment used in games.

24. **(Original)** The film according to claim 1, wherein the film is configured to be sewn into fabric.

25. **(Original)** The film according to claim 1, further comprising:  
a label stock having graphical indicia adhered to the plastic film, such that the graphical indicia is visible.

26.-35. **(Cancelled).**

36. **(Currently Amended)** A silicone elastomer film, comprising:  
a heat-stabilized, plastic film having a surface; and  
a non-molded silicone elastomeric coating disposed on the surface of the film,  
the silicone elastomeric coating having a durometer of less than 30 on the Shore A  
scale disposed on a first surface of the plastic film, the silicone elastomeric coating  
having a bubble pattern texture, each bubble of the bubble pattern texture having a  
height-to-diameter aspect ratio of less than 1.0.
37. **(Previously Presented)** The silicone elastomer film, according to claim 36,  
wherein the heat-stabilized, plastic film exhibits a surface energy of less than about 40  
Dynes/cm.
38. **(Previously Presented)** The silicone elastomer film, according to claim 36,  
wherein the elastomeric coating exhibits a durometer of less than 40 on the Shore A  
scale.
39. **(Previously Presented)** The silicone elastomer film, according to claim 36,  
wherein the elastomeric coating exhibits a durometer of less than 30 on the Shore A  
scale.

40. **(Currently Amended)** A silicone elastomeric film, comprising:

a heat-stabilized, plastic film exhibiting a surface energy of less than about 40 Dynes/cm;

a silicone elastomer layer disposed on a first surface of the heat-stabilized, plastic film, the silicone elastomer layer exhibiting a durometer of less than about ~~[[40]]~~ 30 on the Shore A scale, the silicone elastomer layer defining a plurality of low-profile dimples extending outwardly from an exposed surface of the silicone elastomer layer, each dimple having a height-to-diameter aspect ratio of less than 1.0;

a release liner; and

an adhesive adhered to a second surface of the heat-stabilized, plastic film and releasably adhered to a surface of the release liner.